



UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES DEPARTMENT OF COMMERCE
United States Patent and Trademark Office
Address: COMMISSIONER FOR PATENTS
P.O. Box 1450
Alexandria, Virginia 22313-1450
www.uspto.gov

APPLICATION NO.	FILING DATE	FIRST NAMED INVENTOR	ATTORNEY DOCKET NO.	CONFIRMATION NO.
10/797,223	03/10/2004	Nicholas James Adams	TS5581 (US)	4123
23632	7590	12/06/2007		
SHELL OIL COMPANY P O BOX 2463 HOUSTON, TX 772522463			EXAMINER SINGH, PREM C	
			ART UNIT	PAPER NUMBER
			1797	
			MAIL DATE	DELIVERY MODE
			12/06/2007	PAPER

Please find below and/or attached an Office communication concerning this application or proceeding.

The time period for reply, if any, is set in the attached communication.

**UNITED STATES DEPARTMENT OF COMMERCE****U.S. Patent and Trademark Office**

Address: COMMISSIONER FOR PATENTS

P.O. Box 1450

Alexandria, Virginia 22313-1450

APPLICATION NO./ CONTROL NO.	FILING DATE	FIRST NAMED INVENTOR / PATENT IN REEXAMINATION	ATTORNEY DOCKET NO.
10797223	3/10/2004	ADAMS, NICHOLAS JAMES	TS5581 (US)

SHELL OIL COMPANY
P O BOX 2463
HOUSTON, TX 77252-2463

EXAMINER

Prem C. Singh

ART UNIT	PAPER
----------	-------

1797

102307

DATE MAILED:

Please find below and/or attached an Office communication concerning this application or proceeding.

Commissioner for Patents

Chen et al (Molecular Transport and Reaction in Zeolites, Table 2.1, page 11, John Wiley and Sons, 1994) is attached.

Glenn Cardozo
Supervisory Patent Examiner
Technology Center 1700

Table 2.1 Available Zeolite Structures

IUPAC Code ^a	Zeolite	Channel Size ^b	Comment
-CLO	Cloverite	20' and 8'	Not connected
VFI	VFI-5	18'	
AET	AIPO ₄ -8	14'	
AFI	AIPO ₄ -5	12'	
AFR	SAPO-40	12' and 8'	Interconnected
AFS	MAPSO-46	12' and 8''	Interconnected
AFY	CoAPO-50	12' and 8''	Interconnected
ATO	AIPO ₄ -31	12'	
ATS	MAPO-36	12'	
'BEA'	Beta	12'	
BOG	Boggsite	12' and 10'	Interconnected
BPH	Beryllophosphate-H	12' and 8''	Interconnected
CAN	Cancrinite	12'	
EMT	EMC-2	12'	
FAU	Faujasite	12'''	
GME	Gmelinite	12' and 8''	Interconnected
LTL	Linde Type L	12'	
MAZ	Mazzite	12' and 8'	Not connected
MEI	ZSM-18	12' and 7''	Interconnected
MOR	Mordenite	12' and 8'	Interconnected
MTW	ZSM-12	12'	
OFF	Offretite	12' and 8''	Interconnected
ROG	Roggianite	12'	
AEL	AIPO ₄ -11	10'	
APD	AIPO ₄ -41	10'	
DAC	Dachiardite	10' and 8'	Interconnected
EPI	Epistilbite	10' and 8'	Interconnected
EUO	EU-1	10'	With large side pockets
FER	Ferrierite	10' and 8'	Interconnected
HEU	Heulandite	10' and 8''	Interconnected
LAU	Laumontite	10'	
MEL	ZSM-11	10'	
MFI	ZSM-5	10'	
MFS	ZSM-57	10' and 8'	Interconnected
MTT	ZSM-23	10'	
NES	NU-87	10''	
PAR	Partheite	10'	
STI	Stilbite	10' and 8'	Interconnected
TON	Theta-1	10'	
-WEN	Wenkite	10'' and 8'	Interconnected
-CHI	Chiavennite	9'	
LOV	Lovdarite	9' and 8'	Interconnected
ABW	Li-A	8'	(Barrer and White)
AEI	AIPO ₄ -18	8'	
AFT	AIPO ₄ -52	8'	
APC	AIPO ₄ -C	8''	
APD	AIPO ₄ -D	8''	
ATN	MAPO-39	8'	
ATT	AIPO ₄ -12-TAMU	8''	

[Table of Contents](#)[Introduction and Scope](#)[Zeolite Physical and Chemical](#)[Characteristics](#)[Definition of Zeolites](#)[Application of Zeolites](#)[more »](#)[Definition of Zeolites](#)[References](#)[Definition of Zeolites](#)[References](#)[Measurements](#)[... 0-11](#)[Definition of Zeolites](#)[Principles of Zeolite](#)[Examples of Zeolites](#)[Definition of Zeolites](#)[Impact of Zeolites](#)[Conclusions](#)[Index](#)[Copyright](#)[Wiley.com - Free](#)[Amazon.com](#)

By C. Morris Smith, N.
Y. Chen, Thomas F.
Degnan

Published 1994
John Wiley and Sons

328 pages

ISBN 0471185485